INDEX

1/3



PATENT ABSTRACTS OF JAPAN

(11)Publication number: 2000086217

(43)Date of publication of application: 28.03.2000

(51)Int.CI. CO1B 31/02 B01J 23/28

AGENCY OF IND SCIENCE & (21)Application number: 10267317 (71)Applicant:

TECHNOL

OSHIMA SATORU YUMURA MORIO **UCHIDA KUNIO** IGASAKI FUMIKAZU

KURIKI YASUNORI

OSHIMA SATORU (72)Inventor: (22)Date of filing: 05.09.1998

YUMURA MORIO **UCHIDA KUNIO** IGASAKI FUMIKAZU KURIKI YASUNORI

(54) PRODUCTION OF CARBON NANOTUBE

(57)Abstract:

PROBLEM TO BE SOLVED: To attain a high yield and to enable continuous operation and mass production by decomposing a hydrocarbon at a high temperature on a catalyst comprising metal molybdenum or a metal molybdenum-containing material to deposit carbon nanotubes on the catalyst.

SOLUTION: A catalyst comprising metal molybdenum or a metal molybdenum-containing material, preferably a catalyst obtained by supporting metal molybdenum on an inorganic support is put in a reactor and a hydrocarbon is decomposed in the reactor at 800–1,200° C to deposit carbon nanotubes on the catalyst. The catalyst with the deposited carbon nanotubes is discharged from the reactor. The carbon nanotubes are continuously produced by combining the depositing and discharging steps. In other way, a hydrocarbon oil containing the catalyst is spouted into a reactor kept at 800–1,200° C and the hydrocarbon is decomposed to form carbon nanotubes.

LEGAL STATUS

[Date of request for examination]

05.09.1998

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

3007983

[Date of registration]

03.12.1999

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998 Japanese Patent Office

MENU

SEARCH

INDEX

DETAIL

NEXT